

## SUCCINIMIDE ADDITIVE C-5AB

|  |   |                      |                |
|--|---|----------------------|----------------|
| <b>Specification 38.401-58-130-95</b>                      | <b>Ash-free succinimide dispersant produced on polyisobutylene basis with molecular mass 1000 and modified by boron. It is used in combination with antioxidant and neutralizing additives in the process of oil manufacture for gasoline and diesel engines.</b> |                      |                |
| <b>Characteristics</b>                                     | <b>Minimum</b>  | <b>Typical value</b> | <b>Maximum</b> |
| Kinematic viscosity at 100 °C, mm <sup>2</sup> /sec. (cSt) | -   | 65.0                 | 200.0          |
| Flash point (COC), °C                                      | 160   | 220                  | -              |
| Total base number (TBN), mg KOH/g                          | 10  | 17                   | -              |
| Nitrogen content, % wt.                                    | 1.00  | 1.10                 | -              |
| Boron content, % wt.                                       | 0.30  | 0.45                 | 0.80           |
| <b>Condition of usage</b>                                  | Recommended solution temperature of additive in base oil is up to 80 °C. Any devices providing uniformity of stirring of package of additives in base oil can be used for dissolving. Shelf life at ambient temperature – 24 months.                              |                      |                |
| <b>Safety requirements</b>                                 | Before usage the product please read material safety data sheet (MSDS) of the product.  |                      |                |